

Hydroxyfunctional polyacrylic dispersion

## Technical Data Sheet

Name: Antkote 2057  
Revision Date: 2021-07-02

NO.WHSM\_2057  
Version: 1.1

### Product Description

Antkote 2057 is a hydroxyfunctional polyacrylic dispersion designed for metal baking coating. In combination with amino resins or blocked polyisocyanates, it can be used for high gloss baking coating, especially for metallic coating. Approx. 37% in water/1-butoxy-2-propanol, approx. 56:7. Neutralizing agent, N,N-dimethyl ethanolamine, bound as a salt.

### Properties

1. Excellent orientation of aluminum powder.
2. High thixotropy.
3. High gloss.
4. Excellent water resistance.

### Characteristic data<sup>\*</sup>

Property	Value	Unit	Method
Appearance	Translucent to milky white liquid		
Weight Solids	37±1	%	WHPU/T011-571-2017
pH	7.0-9.0		GB 8325-87
Viscosity	50-8000	mPa·s	Brookfield, LV, 63#, 12rpm, 25°C
OH content	2.6	%	Calculated on solid resin
Density	1.05	g/cm <sup>3</sup>	GB/T 4472-2011

<sup>\*</sup>These properties are typical but do not constitute specifications.

### Storage

The product should be stored in dry conditions above 5°C and below 35°C with the integrity of the packaging, and prevent direct sunlight. The validity of this product is for 12 months, performance assessment is recommended before use after shelf life. The product should be protected from freezing during storage. It is suggested to filter before application and use up once the package is open.

# Antkote 2057



The viscosity of the product is largely governed by the pH. As the pH may decrease during storage, a decrease in viscosity is also to be expected. The viscosity can be adjusted to its original value by the addition of small amounts of an aqueous 10% solution of N,N-dimethyl ethanolamine.

**Disclaimer:** Wanhua Chemical Group Co., LTD. recommends that any customers of this material should check with Materials Safety Data Sheet (MSDS) for details about safely handling this material. We also suggest that you contact the suppliers of any other materials used in our recommended formulations and suggestions for appropriate health and safety regulations prior to use. The information contained herein is believed to be reliable. However, nothing in this technical sheet should be considered as a representation of warranty, express or implicit, regarding the product characteristics, application, quality, safety, merchantability or fitness for a particular purpose. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.